

# TYPICAL PROPERTIES OF COMPOSITION CORK

Natrual Cork

TYPICAL/PHYSICAL PROPERTIES	UNIT OF MEASURE	TEST METHOD	N-106
DENSITY			SOFT
	lbs/cu ft	ASTM D3676	17 min
	g/L	ASTM D3676	272min
COMPRESSION @ 100 PSI	%	ASTM F36	20 to 40
RECOVERY	%	ASTM F36	75 min
TENSILE STRENGTH	PSI	ASTM F152	100 min
FLEXIBILITY	FACTOR	ASTM F147	5max
TEMPERATURE RANGE			-40 to +250°F (-40 to +121°C)
<u>SPECIFICATIONS:</u>			
ASTM F104			F219000
FED HH-C-576B			Type II Class 2
AVAILABLE THICKNESSES			1/32, 3/64, 1/16, 3/32, 1/8, 3/16, 1/4, 5/16, 3/8, 1/2
SHELF LIFE (When protected from enviromental extremes)			2 YEARS

This information is furnished as a guide for selecting materials. Manufacturer disclaims liability for results or use of this information.

It is the customer's responsibility to obtain and test samples when determining suitability of material for a particular application.

Distributed By:

**Advanced Gasket & Supply, Inc.**  
 3336 Stuart Drive Fort Worth, TX 76110  
 Phone: 817.927.0500 Fax: 817.927.0554  
[www.advancedgasket.com](http://www.advancedgasket.com)

Issue date 01-2014